



## TECHNICAL SPECIFICATIONS

### AB-951

**SPECIFICATION ASTM D2000: 1BC706Z1**

**Z1 = HARDNESS 65 +/-5**

**POLYMER: NBR / SBR / CR**

ASTM	DESCRIPTION	VALUE
	SPECIFIC GRAVITY (gr/cc)	1.45
D2240	HARDNESS (Shore A)	65
D412	TENSILE (psi)	600 min.
	ELONGATION (%)	300 min.
D395B	COMPRESSION SET	22 hrs @ 100°C 80% max.
D573	HEAT AGING	70 hrs @ 100°C Changed Hardness: +/- 15 points max. Tensile: +/- 30% max. Elongation: -50% max.
D471	OIL AGING (#3)	70 hrs @ 100°C Volume changed: 120% max.
Temperature Range (general guideline):		-20° to 190°F (-29° to 88°C)
Mullen Burst 1Ply: 300 psi nom.		
Maximum pieces per roll: 2 (Exception 1/32" = 3 pieces)		
Minimum piece length: 5'		
Width tolerance: -0 /+ 1"		
Length tolerance: ± 10%		
Material is within RMA commercial gauge tolerances.		

**Please ensure the product meets your application specification prior to order placement.**

