

Reli-A-Pak® Bolt, Nut, & Gasket Sets by Reliable Fasteners, Inc.

PRODUCT INFO

BILTRITE

Nitrile (Buna-N) Sheet

Style 35 – Commercial

Style	Thickness Inches	Width Inches	Durometer Hardness Shore A ±5	Tensile	Elongation	Temperature	Wt. Per Lin. Foot 36"	Finish	Specifications
35	1/16 thru 1	36 & 48	40	800	350	-20°F to +170°F	1/8-2.5	*Smooth	ASTM D -2000 SAE J200, 1BF 408Z1
35	1/32 thru 1	36 & 48	50	800	300	-20°F to +170°F	1/8-2.6	*Smooth	ASTM D -2000 SAE J200, 1BF 508Z1
35	1/32 thru 1	36 & 48	60	900	300	-20°F to +170°F	1/8-2.6	*Smooth	ASTM D -2000 SAE J200, 1BF 609
35	1/32 thru 1	36 & 48	70	1000	200	-20°F to +170°F	1/8-2.7	*Smooth	ASTM D -2000 SAE J200, 1BF 710
35	1/16 thru 1	36	80	1000	100	-20°F to +170°F	1/8-2.9	*Smooth	ASTM D -2000 SAE J200, 1BF 810

*Also available in Matte Finish.

Z1 Meets basic requirement for BF materials, physical properties are as listed.

RELI-A-PAK® is a registered trademark of Reliable Fasteners, Inc.