

Peroxide Cure EPDM Sheet by West American Rubber Company, LLC

Durometer Hardness Shore A ± 5	Tensile* PSI	Ultimate Elongation* Percent	Temperature Range	Estimated Weight Per Linear Foot (1/8" x 36")	Specifications
40	1550	550	-55°F to +300°F	2.13 lb	ASTM D 2000 4CA 415 A25 B35 C32 EA14 F19
50	1600	400	-55°F to +300°F	2.1 lb	ASTM D 2000 4CA 515 A25 B35 C32 EA14 F19
60	1800	350	-55°F to +300°F	2.15 lb	ASTM D 2000 4CA 615 A25 B35 C32 EA14 F19
70	1700	250	-55°F to +300°F	2.2 lb	ASTM D 2000 4CA 715 A25 B35 C32 EA14 F19
80	1800	200	-55°F to +300°F	2.32 lb	ASTM D 2000 4CA 815 A25 B35 C32 EA14 F19

*Physicals presented are typical values.